

PRODUCT DATA SHEET

SikaCeram[®]-200

High performance polymer-modified, Tile Adhesive

DESCRIPTION

SikaCeram[®] 200 is a polymer modified, cement based, improved adhesive for ceramic and porcelain tiles. It can be used in layers up to 5 mm thick and is suitable for all kind of tiles for inside and outside application for residential and medium load areas.

USES

Suitable for bonding of high absorption ceramic tiles, earthenware, extruded and refined porcelain tiles

- Suitable for bonding of large size tiles used in industrial environment, wet areas, swimming pools, facades
- Suitable for bathrooms, kitchens, balconies, terraces, etc
- Indoor and outdoor application over concrete, cement mortars, bricks and plaster
- For horizontal and vertical areas
- Suitable for moisture tolerant natural stone Suitable to tile directly on various Sika waterproofing products

PRODUCT INFORMATION

Packaging	25 Kg
Appearance / Colour	Grey Powder
Shelf life	12 months minimum from date of production
Storage conditions	Undamaged original sealed packaging, in dry cool conditions
Maximum grain size	0.4 mm
Slip resistance	≤ 0.5 mm

CHARACTERISTICS / ADVANTAGES

- Very good adhesion
- Easy to use with excellent workability and thixotropic consistency
- Good bond strengths
- Non-Toxic
- No vertical slip, high slump resistance and grab
- Suitable for all types of Ceramic and Porcelain tiles

APPROVALS / CERTIFICATES

C1T classified according to EN 12004

Mixing ratio

Add about 7.25 -7.5 liters clean potable water to a 25 kg bag. Mix mechanically using a forced action mixer or slow speed drill (< 500 rpm) and mixing paddle for at least 3 minutes until a homogeneous mix, free of lumps is achieved. Do NOT use a normal free fall concrete mixer. Do not mix more material than can be used within the open time. Leave material to stand in mixing container until the majority of bubbles have dispersed (minimum 10 minutes). Then remix the material for 15 seconds – the product is now ready for use. If open time is exceeded or the adhesive dries prematurely, remove tiles and re-apply using fresh material

Fresh mortar density

About 1.9 kg/litre when wet mix at 250C

Consumption

The consumption depends on the surface profile and roughness of the substrate and the placing technique (simple placing or back-back-“buttering”). One 25 kg bag will cover approximately 5 – 7 m²

Layer thickness

Minimum 2mm
Maximum 5mm

Ambient air temperature

Minimum: +8°C
Maximum: +40°C

Substrate temperature

Minimum: +8°C
Maximum: +35°C

Open Time

25 Minutes

Adjustability time

Once the tiles are set into the mortar, they can be adjusted for up to approximately 30 minutes (at +25°C)

Curing time

Before jointing / grouting works - Min 8 hours
Before opening to light foot traffic - Min 24 hours
Before opening to full traffic - Min 14 days

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

- Cementitious substrates must be strong enough for application of the tiles and the substrates should not continue to shrink after the installation of the tile.
- Do not exceed the recommended water dosage. Apply only to sound, prepared substrates.
- Do not exceed maximum layer thicknesses.
- If additional waterproofing underneath the tiles is required, then the following products can be used: Sika Top® Seal-107, Sika Cemflex, etc. Refer to the relevant product data sheet for more information.
- Protect freshly applied material from rapid drying due to heat, wind etc. and from contact with water or other liquids before the mortar has hardened

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, please refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety related data

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete surface must be clean, sound, level and un-

contaminated by oil or grease. Remove cement limeracies, formwork traces and loosely adhering particles by sand blasting or high pressure water jetting. New concrete block work, render or screed should be allowed to cure for at least 28 days and or until shrinkage movement has completed before fixing tiles. Absorbent substrates must be pre-watered to saturate surface dry(SSD) conditions.

APPLICATION

Apply Sika®Ceram-200 at 2 - 5 mm thickness directly to the concrete substrate, using a notched trowel and spread the mortar evenly over the area to be tiled. Cover only an area that can be tiled within 15 - 30 minutes. Apply with “V”-notched trowels for small tiles. Apply with square notched trowel for bigger tiles. Press tiles firmly into the mortar with a twisting action to ensure optimum adhesion.

CLEANING OF EQUIPMENT

Clean all equipment and tools with water immediately after use. Dry hardened material can be removed mechanically

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kenya Limited

Semco Industrial Park 2nd/ Floor,
Mombasa Road
P.O Box 38645 - 00623 Nairobi, Kenya
Mobile: +254 711 140234
Web: ken.sika.com

Product Data Sheet

SikaCeram®-200
May 2021, Version 01.01
021710102000000054

SikaCeram-200-en-KE-(05-2021)-1-1.pdf

